

HMC 80/100 CCK

Face Stock : C1S – High Gloss Paper - 80 GSM \pm 10%

Adhesive : Acrylic Emulsion.


Base Stock : Clay Coated Paper – 85 GSM \pm 10%

Adhesive Coat Weight : 20 GSM \pm 10%.

Loop Value : Above 600 Grams/Sq.inch

Shear Value : Between 50 to 100 Minutes (Suspended Weight – 1 kg)

Peel Value : 1200-1600 Grams/inch.



PRINT APPLICATION			
OFFSET	FLEXO	BARCODE	DIGITAL
✓	NR	NR	NR
NR – NOT RECOMMENDED			